



ANTI-GRAVEL SPRAY

EAN code: 5907588403238 item no.: 001002 white

EAN code: 5907588402606 item no.: 001004 grey

EAN code: 5907588480017 item no.: 001006 black



PROPERTIES

The car body protection agent is a synthetic resin based agent. It forms a flexible coating that perfectly protects against stone chips and mechanical influences. It is used to protect door sills, bumpers, spoilers and other car body parts. The product has a very high abrasion resistance (resistance against stones). It can be lacquered with all lacquer systems.



COLOUR



white



grey



black



METHOD OF USE

Thoroughly clean and degrease and then dry the areas to be coated. Cover adhering surfaces with paper. Shake the container well for about 3 minutes before use. When painting, keep the container at a distance of 15-20 cm from the surface to be coated. After use, invert the container and spray until the valve is empty.



SURFACE

- **metal** - prime, sand, blast and degrease with "BOLL Silicone remover" and then apply the next coat.
- **non-ferrous metals (zinc, aluminium, copper, etc.)** - prime, sand down, blow off and degrease with "BOLL Silicone remover" and then apply the next coat.
- **reactive primer** - apply another coat when dry.
- **epoxy primer** - can be used to isolate materials. After sanding with P320, blow off, degrease with "BOLL silicone remover" and then apply another coat.
- **two-component acrylic primer** - apply varnish or control powder. After sanding P240-P320, blow off, degrease with "BOLL silicone remover" and then apply another coat.
- **polyester putties** - sand P20-P320, blow off and degrease with "BOLL Silicone remover", then apply another coat.



INFORMATION

Do not spray toward engine, transmission, brake parts or exhaust system. CAN BE VARNISHED.



APPLICATION



Thoroughly clean and mat the surface



Thoroughly clean and degrease the surface



For corroded surfaces, we suggest using BOLL rust neutralizer or BOLL anticorrosive paint




Mix thoroughly



Apply 2 to 3 coats from a distance of 15-20 cm



Evaporation time between coats: 5 ÷ 10 minutes



Recommended coating thickness approximately 1mm



The surface can be painted after approx. 3 hours
For water-based paints - after approx. 24 hours



After use, invert the container and spray until the valve is empty



PHYSICAL PROPERTIES

density (at 20°C):	0,805 g/cm ³
boiling point:	- 44°C
flash point:	< 0°C
flash point:	200°C
explosive limits:	upper: 11,5% v/v. / lower: 0,8% v/v.



STORAGE CONDITIONS



Protect the product from excessive heat and cold. Avoid direct exposure to sunlight. Store in a dry place.



SHELF LIFE

Two years from the date of production on the packaging.



SAFETY

See Safety Data Sheet.



OTHER INFORMATION

All technical data are approximate values. We advise you to test the material to ensure suitability for your specific application. The producer reserves the right to improve the product and change the technical conditions with the possibility of making changes inside the specification.