



## RUST CONVERTOR

EAN code: 5907588408578 item no.: 00140194 cap. 60ml  
EAN code: 5907588406093 item no.: 00140193 cap. 250ml



### PROPERTIES

It is a product based on high quality epoxy resins. Thanks to its formulation it has excellent priming and anticorrosive properties. At the same time it serves as a primer and a base for subsequent coats, which can be various types of paints, varnishes and polyester putties. It has a wide variety of applications and can be applied directly to rust. Actively works on rust with the formation of blocking organic iron compounds and a protective epoxy coating against corrosion.



### COLOUR



amber



### METHOD OF USE

Remove mechanically loose rust fragments, clean, degrease with "BOLL Silicone remover" and then dry the covered surface. Shake the container for about 2 minutes before use. Depending on the degree of corrosion, it is recommended to apply 3 - 4 layers of the product using a brush, roller or spray gun. Can be painted with most paints and topcoats after 12 hours at a temp. ambient 20°C. It is recommended to carry out a test to check the compatibility of the product in a given application.



### APPLICATION



Thoroughly clean and mat the surface



Thoroughly clean and degrease the surface



Shake the bottle well before use



Apply the preparation evenly on the rusted surface.  
Depending on the degree of corrosion, it is recommended to apply 3 - 4 layers of the product.



Evaporation time between coats: 5 ÷ 10 minutes



Can be painted with most paints and topcoats after 12 hours at a temp. ambient 20°C



## PHYSICAL PROPERTIES

viscosity:	min. 30sec. Ford4
dust dry:	approx. 20 min. at temp. 20°C
density:	0,930 g/cm <sup>3</sup>
application temperature:	10-25°C/ relative humidity 45-60%



## STORAGE CONDITIONS



Protect the product from excessive heat and cold. Avoid direct exposure to sunlight. Store in a dry place.



## SHELF LIFE

Two years from the date of production on the packaging.



## SAFETY

See Safety Data Sheet.



## OTHER INFORMATION

All technical data are approximate values. We advise you to test the material to ensure suitability for your specific application. The producer reserves the right to improve the product and change the technical conditions with the possibility of making changes inside the specification.