



## FINISH PUTTY

EAN code: 5907588408585 item no.: 002010 cap. 250g  
EAN code: 5907588408592 item no.: 002011 cap. 500g  
EAN code: 5907588410878 item no.: 0020111 cap. 1,0kg  
EAN code: 5907588408608 item no.: 002012 cap. 1,8kg

**+** PROPERTIES

Soft polyester putty for filling scratches and minor damages. Ideally suited for manual and mechanical sanding. It has high flexibility and very good adhesion to various surfaces.

**•••** COLOUR

 light grey

**=** SURFACE

- **steel** - degrease, grind, blow, and degrease again with "BOLL Silicone remover", then apply another coat.

---

- **aluminium** - degrease, sand, blow, and degrease again with "BOLL Silicone remover", then apply another coat.

---

- **old paint coatings** - sand with P220-P280, blow, and degrease with "BOLL Silicone remover", then apply the next coat.

---

- **two-component acrylic primer** - sand with P220-P280, blow, and degrease with "BOLL silicone remover", then apply the next coat.

---

- **polyester laminates** - sand with P80-P120, blow, and degrease with "BOLL Silicone remover", then apply another coat.

**☰** INFORMATION

The putty should not be applied directly on wash primers or one-component acrylic and nitrocellulose products.



## APPLICATION



Thoroughly clean and mat the surface



Thoroughly clean and degrease the surface




**Mixing ratio**                      **by weight**

<b>putty</b>	100 g
<b>hardener</b>	2-3 g

Stir thoroughly until uniform in colour. Do not exceed the recommended amount of hardener.  
Mixture life: 4-6 minutes at 20°C



Apply with a spatula in several thin layers up to a total thickness of 3mm.



Drying time: 20-30 minutes at 20°C



IR illuminator: heat for 4 to 6 minutes. Do not exceed a temperature of 60°C.



**Preliminary grinding:** P180-P240

**Finishing grinding:** P240-P320

Coverage:

- 2-component polyester putties
- 2-component polyester spray putties
- 2-component acrylic primers
- 2-component epoxy primers



## PHYSICAL PROPERTIES

density at 20°C:	1,70 – 1,90 g/cm <sup>3</sup>
solubility in water:	very slight
viscosity:	210 000 - 370 000 mPa*s
VOC content:	< 250 g/l (permissible: 250 g/l)



## EQUIPMENT CLEANING

Wash immediately after application with nitrocellulose thinner or thinner for acrylic products..



## STORAGE CONDITIONS



Protect the product from excessive heat and cold. Avoid direct exposure to sunlight. Store in a dry place.



## TERMIN PRZYDATNOŚCI

24 months from the production date placed on the packaging.



## SAFETY

See Safety Data Sheet.



## OTHER INFORMATION

All technical data are approximate values. We advise you to test the material to ensure suitability for your specific application. The producer reserves the right to improve the product and change the technical conditions with the possibility of making changes inside the specification.