

## CLEAR COAT VHS 2:1

EAN code: 5907588409100 item no.: 001664

EAN code: 5907588409117 item no.: 001665 hardener STANDARD

EAN code: 5907588410120 item no.: 0016651 hardener FAST



### PROPERTIES

Top-grade VHS clearcoat (VeryHighSolid). It has a very high scratch resistance and the highest gloss. The product has a very high performance due to the high content of solids. The varnish allows you to get any structure and copy OEM painting. Does not require the use of a thinner.



### COLOUR

clear









### SURFACE

Can be applied over most available solvent and waterborne basecoats.



### APPLICATION

	Mixing ratio:	by volume		by mass	
	clear coat		2		100g
	hardener STANDARD		1		52g
	hardener FAST		1		51g
	Viscosity:				
	DIN 4 20°C 18 - 22 s				
	Mixture life				
	hardener STANDARD		hardener FAST		
	20°C	1,5 h	20°C	1h	
	Nozzle	1,2 - 1,3 mm			
	Pressure	1,2 – 2,5 bar			
	Number of layers	2 layers			
	Evaporation time 5 - 10 min				
		20°C		60°C	
		STANDARD	FAST	STANDARD	FAST
	Dust free	30 min	20 min	5 min	5 min
	Operating hardness	12 h	9 h	30 min + 2h/20°C	20 min + 2h/20°C
	Overall hardness	36 h	28 h	30 min + 24h/20°C	20 min + 2h/20°C



Short waves  
max 90°C  
8 - 12 min



#### STORAGE CONDITIONS



Protect the product from excessive heat and cold. Avoid direct exposure to sunlight. Store in a dry place.



#### SHELF LIFE

24 months from the production date placed on the packaging.



#### SAFETY

See Safety Data Sheet.



#### OTHER INFORMATION

All technical data are approximate values. We advise you to test the material to ensure suitability for your specific application. The producer reserves the right to improve the product and change the technical conditions with the possibility of making changes inside the specification.