



UNDERBODY COATING



EAN code: 5907588460019 item no.: 001007 black



PROPERTIES

This bitumen rubber-based underbody preservative forms a flexible film that perfectly protects the underbody of your car against stone chips, salt, water and mechanical influences. It is resistant to gritting salt and industrial fumes. It also acts as a sound absorber.



COLOUR



black



METHOD OF USE

The underbody preservative can be easily applied by airless spray guns. Thoroughly clean and degrease and then dry the areas to be conserved. Cover adhering surfaces with paper. Shake the container well for about 3 minutes before use. Best results are achieved at a pressure of 3 to 6 bar.



SURFACE

- **two-component acrylic primer** - apply varnish or control powder. After sanding, blow off, degrease with "BOLL silicone remover" and then apply another coat.
- **epoxy primer** - can be used to isolate materials. After sanding, blow off, degrease with "BOLL silicone remover" and then apply another coat.
- **polyester putties** - sand, blow off and degrease with "BOLL Silicone remover" and then apply the next coat.



INFORMATION

Do not spray toward engine, transmission, brake parts or exhaust system. CAN BE VARNISHED.



APPLICATION



Thoroughly clean and mat the surface



Thoroughly clean and degrease the surface



For corroded surfaces, we suggest using BOLL rust neutralizer or BOLL anticorrosive paint.



Mix thoroughly



Apply in 1 or 2 coats at 3-6 bar



Evaporation time between coats: 5 ÷ 10 minutes



Drying time about 24 hours



Close the container tightly after use



PHYSICAL PROPERTIES

density (at 20°C):	1,04 g/cm ³
boiling point:	142°C
flash point:	21-55°C
flash point:	450°C
flammability limits:	upper: 7,5 % vol. / lower: 0,6 % vol.



EQUIPMENT CLEANING

Wash the gun with nitrocellulose solvent (Nitro) or white spirit.



STORAGE CONDITIONS



Protect the product from excessive heat and cold. Avoid direct exposure to sunlight. Store in a dry place.



SHELF LIFE

Two years from the date of production on the packaging.



SAFETY

See Safety Data Sheet.



OTHER INFORMATION

All technical data are approximate values. We advise you to test the material to ensure suitability for your specific application. The producer reserves the right to improve the product and change the technical conditions with the possibility of making changes inside the specification.